

Product Description

Polyimide (PI) have excellent properties of high temperature resistance, mechanical performance, electrical and thermal insulation, flame retardance, radiation resistance, and solvent resistance. The material is available as chopped or staple fibers and as filament.

These products are manufactured through dry spinning process. PBP (product by process) management system is adopted to strictly control the quality of the products according to ISO9001:2008/ISO14001:2004

Typical PI Chopped Fiber

Type: 0.78 ~ 6dtex
Cut Lengths: 3mm, 6mm, 12mm
Color: original color (golden yellow)



Typical PI Staple Fiber

Type: 0.78 ~ 6dtex
Cut Lengths: 38mm, 51mm, 65mm, 76mm
Color: golden yellow, black, dark green, navy, tangerine



Typical PI Filaments

Type: 90~3300D, 1.67~3.3dtex each thread
Tenacity of each thread: 4~7cN/dtex
Color: golden yellow, black, dark green, navy, tangerine



Note: the type and cut length of above products can be as per requirement

Dexnyl[®] PI Fiber Characteristics

Item	Unit	Value
Finess	dtex	0.78~6
Length	mm	3~76
Density	g/cm ³	1.41
Tenacity	cN/dtex	4~6
Elongation	%	10~30
Suggested long-term working Temp.	°C	260~300
Initial decomposition Temp.	°C	567
Limiting Oxygen Index (LOI)	%	38
Shrinkage at 280 °C, 24h	%	<1

Hydrolysis Resistance

Dexnyl[®] PI Fiber adopts dry spinning method. The fiber has good hydrolysis resistance property. The retention rate of tenacity is 82.58% which is far higher than allied fibers.

Item	Original tenacity (cN/dtex)	Tenacity after vapour treatment (140°C, 24h)	Retention rate
Dexnyl [®] PI Fiber	4.97	4.10	82.58%
Other PI	3.69	3.59	43.09%

Flame Retardant (FR) Property

Limiting Oxygen Index (LOI)

The LOI indicates the level of oxygen required to keep the material burning after ignition. Dexnyl[®] PI Fiber is classified as non-flammable in atmospheric conditions. The LOI is above 38%

Common FR fiber	Dexnyl [®] PI Fiber	Meta-aramid (PMIA)	PPS	PSA
LOI	>38	28~30	34	33



Datasheet
Dexnyl® PI Fiber_17

Low Damaged Length in Combustion Test

In vertical combustion test under Chinese fire protection criteria GA 10-2014, the damaged length of Dexnyl® PI Fiber fabric is 1/5 of the aramid IIIA fabric (the mainstream FR Fabric). The test result is far above the standard protective fabric.

Item	100% Dexnyl © PI Fiber	Aramid. IIIAA	50% Dexnyl © PI Fiber + 50% FR viscose	50% m-aramid + 50% FR viscose
Damaged length in Warp (mm; 25 times wash)	10	46	12	60
Damaged length in Weft (mm; 25 times wash)	8	48	13	57

No melt and drop, ultralow smoke and non-toxic after carbonization

Dexnyl® PI Fiber will carbonize without melt and drop in case of fire. FR fabric made of Dexnyl® PI Fiber passed the combustion test based on BSS 7238, 7239. There is ultralow smoke and no toxic after carbonization. The density of smoke is 1/200 of the ABD0031 airbus requirement. Dexnyl® PI Fiber is wonderful textile material for confined space, home textiles and protective products.

Dexnyl © PI Fiber Toxic Comparison						(Unit: ppm)	
	Smoke Density (Dm)	CO	HCN	HF	HCl	SO ₂	NO _x
Dexnyl © PI Fiber	1	32	0.7	<0.5	<1	<0.5	<2
Airbus Standard	200	3500	150	100	150	100	100

Antibacterial Property

Dexnyl® PI Fiber has natural antibacterial function. The antibacterial effect outperforms bamboo fiber.

Test Item	Strain	Result
Rate of Antibacteria	Staphylococcus Aureus	71%
	Colibacillus	76%



Datasheet Dexnyl[®] PI Fiber_17

Far IR Property

Far-infrared healthcare textile can promote blood circulation and metabolism, enhance immunity. Dexnyl[®] PI Fiber fabrics meet the international standard for the far-infrared healthcare product with a far infrared ray of 4~16 μ m and normal emittance of 88%.

Test Item	Standard	Test Result
Normal emittance	≥ 0.80	0.88
Wavelength (μ m)	4~16	4~16

Distributed by

BIEGLO GmbH

Bahrenfelder Straße 242
22765 Hamburg
+49 40 4011 30000
info@bieglo.com
www.bieglo.com

The specified values are established from average values of several tests and they correspond to our today's knowledge. They are only to be used as information about our products and as help for the material selection. With these values, we do not ensure specific properties, or the suitability for certain application, therefore we do not assume any legal responsibility for an improper usage. The used test pieces have been machined from extruded semi-finished material. Since the properties depend on the manufacturing process, the actual properties of a specific product may slightly deviate from the tested ones. For information about divergent properties do not hesitate to contact us. On request we advise you regarding the most appropriate component design and the definition of material specifications more suitable to your application data. Notwithstanding, the customer bears all the responsibility for the thorough examination of suitability, efficiency, efficacy and safety of the chosen products in pharmaceutical applications, medical devices or other end uses. Version: Sept 2019